

# WEICONLOCK® type selection chart

| Typ-No.                                       | Pictogram | Application  | Colour      | For threaded joints up to | Viscosity at +25°C in mPa.s Brookfield | Gap filling capacity in mm max. | Breakaway strength Nm (Thread*) | Prevailing strength Nm (Thread*) | Shear strength** Nmm² / (psi) (DIN 54452) | Handling strength at room temperature | Final strength at room temperature | Temperature resistance °C / (°F) | Strength values based on M 10 screws, 8.8 grade, thickness of nut 0.8 d   |
|---|-----------|--|-------------|---------------------------|--|---------------------------------|---------------------------------|----------------------------------|---|---------------------------------------|------------------------------------|----------------------------------|---|
| <b>Threadlocking</b>                          |           |  |             |                           |  |                                 |                                 |                                  |   |                                       |                                    |                                  |   |
| <b>AN 301-43</b>                              |           | Threadlocking, drinking water <sup>1</sup> and DVGW <sup>2</sup> approval, higher viscosity, medium strength, disassembly with normal tools  | blue        | M 36                      | 2.000 - 8.000 mt                       | 0,25                            | 18 - 22                         | 9 - 11                           | 10 - 13 (1.450 - 1.885)                   | 5 - 15                                | 1 - 3                              | -60 to +150 (-76 to +302)        | * Static shear strength based on cylindrical parts of thread Ø 10 mm, tolerance Ø = +0.05 mm, l <sub>0</sub> = 0.88 |
| <b>AN 301-70</b>                              |           | Threadlocking, drinking water <sup>1</sup> approval, medium viscosity, high strength, hard to disassemble  | green       | M 25                      | 500 - 900 nt                           | 0,15                            | 25 - 35                         | 40 - 50                          | 14 - 20 (2.030 - 2.900)                   | 5 - 15                                | 5 - 10                             | -60 to +150 (-76 to +302)        |   |
| <b>AN 302-21</b>                              |           | Threadlocking, vibration-proof; low viscosity, low strength, easy disassembly  | purple      | M 12                      | 125                                    | 0,10                            | 7 - 10                          | 3 - 6                            | 4 - 7 (580 - 1.015)                       | 10 - 20                               | 3 - 6                              | -60 to +150 (-76 to +302)        |   |
| <b>AN 302-22</b>                              |           | Threadlocking, vibration-proof; medium viscosity, low strength, easy disassembly   | purple      | M 36                      | 1.000 mt                               | 0,20                            | 4 - 8                           | 2 - 4                            | 3 - 5 (435 - 725)                         | 10 - 20                               | 3 - 6                              | -60 to +150 (-76 to +302)        |   |
| <b>AN 302-40</b>                              |           | Threadlocking, vibration-proof; DVGW <sup>2</sup> approval, medium viscosity, medium strength, disassembly with normal tools   | transparent | M 20 R ¾"                 | 600 nt                                 | 0,15                            | 12 - 16                         | 18 - 24                          | 8 - 12 (1.160 - 1.740)                    | 10 - 20                               | 3 - 6                              | -60 to +150 (-76 to +302)        |   |
| <b>AN 302-41</b>                              |           | Threadlocking; low viscosity, medium strength, disassembly with normal tools   | blue        | M 12                      | 125 nt                                 | 0,10                            | 10 - 15                         | 12 - 16                          | 8 - 12 (1.160 - 1.740)                    | 10 - 20                               | ca. 3                              | -60 to +150 (-76 to +302)        |   |
| <b>AN 302-42</b>                              |           | Threadlocking; drinking water <sup>1</sup> approval, medium viscosity, medium strength, disassembly with normal tools  | blue        | M 36                      | 1.000 mt                               | 0,20                            | 14 - 18                         | 5 - 8                            | 8 - 12 (1.160 - 1.740)                    | 10 - 20                               | 3 - 6                              | -60 to +150 (-76 to +302)        |   |
| <b>AN 302-43</b>                              |           | Universal threadlocking type; drinking water <sup>1</sup> and DVGW <sup>2</sup> approval, higher viscosity, medium strength, disassembly with normal tools   | blue        | M 36                      | 2.000 - 7.000 mt                       | 0,25                            | 17 - 22                         | 8 - 12                           | 9 - 13 (1.305 - 1.885)                    | 10 - 20                               | 1 - 3                              | -60 to +200 (-76 to +392)        |   |
| <b>AN 302-44</b>                              |           | Threadlocking, drinking water <sup>1</sup> and DVGW <sup>2</sup> approval, higher viscosity, medium strength, easy disassembly   | blue        | M 36                      | 3.000 - 8.000 mt                       | 0,25                            | 8 - 12                          | 5 - 8                            | 9 - 13 (1.305 - 1.885)                    | 20 - 40                               | 4 - 8                              | -60 to +200 (-76 to +392)        |   |
| <b>AN 302-50</b>                              |           | Locking of threads and stud bolts; medium viscosity, high strength, hard to disassemble  | transparent | M 20 R ¾"                 | 500 nt                                 | 0,15                            | 30 - 35                         | 55 - 70                          | 25 - 35 (3.625 - 5.075)                   | 2 - 5                                 | 2 - 4                              | -60 to +175 (-76 to +347)        |   |
| <b>AN 302-60</b>                              |           | Threadlocking for passive materials such as stainless steel, aluminum, etc. - fast bonding without activator; medium viscosity, high strength, hard to disassemble   | green       | M 20 R ¾"                 | 700 - 1.000 nt                         | 0,15                            | 30 - 35                         | 55 - 70                          | 25 - 35 (3.625 - 5.075)                   | 2 - 5                                 | 2 - 4                              | -60 to +200 (-76 to +392)        |   |
| <b>AN 302-62</b>                              |           | Threadlocking; high viscosity, high strength, hard to disassemble  | red         | M 36                      | 1.500 - 6.500 mt                       | 0,25                            | 20 - 25                         | 40 - 55                          | 10 - 15 (1.450 - 2.175)                   | 10 - 20                               | 3 - 6                              | -60 to +150 (-76 to +302)        |   |
| <b>AN 302-70</b>                              |           | Locking of threads and stud bolts; drinking water <sup>1</sup> and DVGW <sup>2</sup> approval, medium viscosity, high strength, hard to disassemble  | green       | M 20 R ¾"                 | 500 nt                                 | 0,15                            | 28 - 35                         | 50 - 65                          | 15 - 20 (2.175 - 2.900)                   | 10 - 20                               | 3 - 6                              | -60 to +200 (-76 to +392)        |   |
| <b>AN 302-71</b>                              |           | Locking of threads and stud bolts; medium viscosity, high strength, hard to disassemble  | red         | M 20 R ¾"                 | 500 nt                                 | 0,15                            | 28 - 35                         | 50 - 65                          | 15 - 20 (2.175 - 2.900)                   | 10 - 20                               | 3 - 6                              | -60 to +150 (-76 to +302)        |   |
| <b>AN 302-72</b>                              |           | Locking of threads and stud bolts; drinking water <sup>1</sup> and DVGW <sup>2</sup> approval, high temperature resistant, higher viscosity, high strength, hard to disassemble  | red         | M 56 R ½"                 | 6.000 - 15.000 mt                      | 0,30                            | 20 - 30                         | 40 - 75                          | 10 - 15 (1.450 - 2.175)                   | 20 - 40                               | 5 - 10                             | -60 to +230 (-76 to +446)        |   |
| <b>AN 302-90</b>                              |           | Threadlocking, for locking after mounting and sealing of hair cracks; low viscosity, high strength, hard to disassemble  | green       | M 5 kapillar              | 10 - 20                                | 0,07                            | 15 - 25                         | 30 - 40                          | 8 - 12 (1.160 - 1.740)                    | 5 - 20                                | ca. 3                              | -60 to +150 (-76 to +302)        |   |
| <b>Sealing of threaded pipes and fittings</b> |           |  |             |                           |  |                                 |                                 |                                  |   |                                       |                                    |                                  |   |
| <b>AN 301-65</b>                              |           | Pipe and flange sealing (with PTFE), drinking water <sup>1</sup> approval, high viscosity, medium strength, disassembly with normal tools  | white       | M 80 R 3"                 | 180.000 - 300.000                      | 0,50                            | 4 - 8                           | 1 - 3                            | 2 - 6 (290 - 870)                         | 10 - 20                               | 24                                 | -60 to +150 (-76 to +302)        |   |
| <b>AN 301-72</b>                              |           | Pipe and flange sealing (with PTFE), drinking water <sup>1</sup> and DVGW <sup>2</sup> approval, high viscosity, medium strength, disassembly with normal tools  | white       | M 80 R 3"                 | 15.000 - 60.000 ht                     | 0,30                            | 5 - 10                          | 4 - 6                            | 5 - 7 (725 - 1.015)                       | 15 - 30                               | 6 - 12                             | -60 to +200 (-76 to +392)        |   |
| <b>AN 302-25</b>                              |           | Sealing of threaded pipes and fittings, vibration-proof; high viscosity, low strength, easy disassembly  | brown       | M 80 R 3"                 | 6.000 - 30.000 mt                      | 0,30                            | 5 - 8                           | 2 - 4                            | 3 - 5 (435 - 725)                         | 15 - 30                               | 3 - 6                              | -60 to +150 (-76 to +302)        |   |
| <b>AN 302-45</b>                              |           | Sealing of threaded pipes and fittings for coarse threaded connections; DVGW <sup>2</sup> approval, high viscosity, medium strength, disassembly with normal tools   | blue        | M 80 R 3"                 | 6.000 - 30.000 mt                      | 0,30                            | 10 - 15                         | 12 - 18                          | 8 - 12 (1.160 - 1.740)                    | 15 - 30                               | 3 - 6                              | -60 to +150 (-76 to +302)        |   |
| <b>AN 302-75</b>                              |           | Sealing of threaded pipes and fittings for coarse threaded parts and flanges; BAM <sup>3</sup> , high viscosity, high strength, hard to disassemble  | green       | M 80 R 3"                 | 14.000 - 24.000 mt                     | 0,30                            | 40 - 50                         | 40 - 50                          | 15 - 25 (2.175 - 3.625)                   | 15 - 30                               | 3 - 6                              | -60 to +150 (-76 to +302)        |   |
| <b>AN 302-77</b>                              |           | Sealing of threaded pipes and fittings for coarse threaded parts and flanges; high viscosity, high strength, hard to disassemble   | red         | M 36                      | 6.000                                  | 0,25                            | 30 - 40                         | 10 - 15                          | 35 - 45 (5.075 - 6.525)                   | 40 - 60                               | 6 - 12                             | -60 to +150 (-76 to +302)        |   |
| <b>AN 302-80</b>                              |           | Sealing of threaded pipes and fittings for passive materials such as stainless steel, aluminum, etc. - fast bonding without activator; higher viscosity, high strength, hard to disassemble                                  | green       | M 36                      | 3.000 - 6.000 mt                       | 0,20                            | 35 - 45                         | 50 - 70                          | 20 - 30 (2.900 - 4.350)                   | 2 - 5                                 | 2 - 4                              | -60 to +200 (-76 to +392)        |   |
| <b>AN 305-11</b>                              |           | Sealing of threaded pipes and fittings; drinking water <sup>1</sup> and DVGW <sup>2</sup> approval, higher viscosity, medium strength, disassembly with normal tools   | white       | M 80 R 3"                 | 17.000 - 50.000 ht                     | 0,40                            | 7 - 10                          | 2 - 4                            | 4 - 6 (580 - 870)                         | 20 - 40                               | 5 - 10                             | -60 to +150 (-76 to +302)        |   |
| <b>AN 305-42</b>                              |           | Sealing of hydraulic and pneumatic systems, universal product; DVGW <sup>2</sup> approval, medium viscosity, medium strength, disassembly with normal tools  | brown       | M 20 R ¾"                 | 500 nt                                 | 0,15                            | 12 - 15                         | 18 - 22                          | 8 - 12 (1.160 - 1.740)                    | 10 - 20                               | 2 - 4                              | -60 to +150 (-76 to +302)        |   |
| <b>AN 305-67</b>                              |           | Pipe and flange sealing (with PTFE) high viscosity, low strength, easy disassembly   | white       | M 80 R 3"                 | 170.000 - 410.000                      | 0,50                            | 3 - 5                           | 2 - 4                            | 6 - 8 (870 - 1.160)                       | 120 - 240                             | 24 - 72                            | -50 to +175 (-58 to +347)        |   |
| <b>AN 305-72</b>                              |           | Pipe and flange sealing (with PTFE), instant seal, drinking water <sup>1</sup> , DVGW <sup>2</sup> and AGA <sup>4</sup> approval, high viscosity, medium strength, disassembly with normal tools                             | white       | M 80 R 3"                 | 17.000 - 50.000 ht                     | 0,40                            | 7 - 10                          | 2 - 4                            | 4 - 6 (580 - 870)                         | 20 - 40                               | 5 - 10                             | -60 to +150 (-76 to +302)        |   |
| <b>AN 305-77</b>                              |           | Universal sealing type for pipes and fittings; drinking water <sup>1</sup> , DVGW <sup>2</sup> and AGA <sup>4</sup> approval, BAM <sup>3</sup> , WRAS, high viscosity, medium strength, disassembly with normal tools        | yellow      | M 80 R 3"                 | 24.000 - 70.000 ht                     | 0,50                            | 18 - 22                         | 10 - 14                          | 6 - 13 (870 - 1.885)                      | 15 - 30                               | 1 - 3                              | -60 to +150 (-76 to +302)        |   |
| <b>AN 305-78</b>                              |           | Pipe and flange sealing for passive materials, drinking water <sup>1</sup> and DVGW <sup>2</sup> approval, BAM <sup>3</sup> , high viscosity, medium strength, disassembly with normal tools                                 | yellow      | M 80 R 3"                 | 50.000 - 80.000 ht                     | 0,50                            | 11 - 16 <sup>5</sup>            | 4 - 7 <sup>2</sup>               | 6 - 13 (870 - 1.885)                      | 25 - 50 <sup>2</sup>                  | 4 - 8 <sup>2</sup>                 | -60 bis +150 (-76 bis +302)      |   |
| <b>AN 305-86</b>                              |           | Pipe sealing, extra strong higher viscosity, hard to disassemble   | red         | M 56 R 2"                 | 6.000 - 7.000 nt                       | 0,30                            | 15 - 30                         | 25 - 45                          | 10 - 20 (1.450 - 2.900)                   | 60 - 90                               | 12 - 24                            | -60 to +150 (-76 to +302)        |   |
| <b>Retaining cylindrical assemblies</b>       |           |  |             |                           |  |                                 |                                 |                                  |   |                                       |                                    |                                  |   |
| <b>AN 301-38</b>                              |           | Retaining cylindrical assemblies, drinking water <sup>1</sup> approval, medium viscosity, high strength, hard to disassemble   | green       | M 36                      | 2.000 - 3.000 mt                       | 0,20                            | 30 - 40                         | 45 - 60                          | 20 - 25 (2.900 - 3.625)                   | ca. 5                                 | 2 - 4                              | -60 to +150 (-76 to +302)        |   |
| <b>AN 301-48</b>                              |           | Retaining cylindrical assemblies, drinking water <sup>1</sup> and DVGW <sup>2</sup> approval, medium viscosity, high strength, hard to disassemble   | green       | M 20 R ¾"                 | 450 - 650 nt                           | 0,15                            | 25 - 30                         | 40 - 55                          | 25 - 30 (3.625 - 4.350)                   | 2 - 6                                 | 2 - 4                              | -60 to +175 (-76 to +347)        |   |
| <b>AN 306-00</b>                              |           | Retaining cylindrical assemblies, low viscosity, high strength, hard to disassemble  | transparent | M 20 R ¾"                 | 500 nt                                 | 0,15                            | 30 - 35                         | 55 - 70                          | 25 - 35 (3.625 - 5.075)                   | 2 - 5                                 | 2 - 4                              | -60 to +175 (-76 to +347)        |   |
| <b>AN 306-01</b>                              |           | Retaining cylindrical assemblies, low viscosity, high strength, hard to disassemble  | green       | M 12                      | 125 nt                                 | 0,10                            | 25 - 30                         | 50 - 60                          | 15 - 18 (2.175 - 2.610)                   | 10 - 20                               | 2 - 4                              | -60 to +150 (-76 to +302)        |   |
| <b>AN 306-03</b>                              |           | Retaining cylindrical assemblies, low viscosity, high strength, hard to disassemble  | green       | M 12                      | 125 nt                                 | 0,10                            | 25 - 30                         | 50 - 60                          | 15 - 18 (2.175 - 2.610)                   | 10 - 20                               | 2 - 4                              | -60 to +150 (-76 to +302)        |   |
| <b>AN 306-10</b>                              |           | Retaining cylindrical assemblies, for passive materials such as stainless steel, aluminum, etc. - fast bonding without activator; drinking water <sup>1</sup> approval, medium viscosity, high strength, hard to disassemble | green       | M 20 R ¾"                 | 700 - 1.000 nt                         | 0,15                            | 30 - 35                         | 55 - 70                          | 25 - 35 (3.625 - 5.075)                   | 2 - 5                                 | 2 - 4                              | -60 to +200 (-76 to +392)        |   |
| <b>AN 306-20</b>                              |           | Retaining cylindrical assemblies, drinking water <sup>1</sup> and DVGW <sup>2</sup> approval, BAM <sup>3</sup> , WRAS, high-temperature resistant; higher viscosity, high strength, hard to disassemble                      | green       | M 56 R 2"                 | 3.000 - 6.000 nt                       | 0,20                            | 28 - 36                         | 40 - 55                          | 15 - 25 (2.175 - 3.625)                   | 20 - 40                               | ca. 24                             | -60 to +200 (-76 to +392)        |   |
| <b>AN 306-30</b>                              |           | Retaining cylindrical assemblies, for passive materials such as stainless steel, aluminum, etc. - fast bonding without activator; BAM <sup>3</sup> , higher viscosity, high strength, hard to disassemble                    | green       | M 36                      | 3.000 - 6.000 mt                       | 0,20                            | 35 - 45                         | 50 - 70                          | 20 - 30 (2.900 - 4.350)                   | 2 - 5                                 | 2 - 4                              | -60 to +200 (-76 to +392)        |   |
| <b>AN 306-38</b>                              |           | Retaining cylindrical assemblies under high dynamical stress, fast-curing; drinking water <sup>1</sup> approval, medium viscosity, high strength, hard to disassemble  | green       | M 36                      | 2.500 mt                               | 0,20                            | 35 - 45                         | 50 - 70                          | 25 - 30 (3.625 - 4.350)                   | ca. 5                                 | 1 - 3                              | -60 to +150 (-76 to +302)        |   |
| <b>AN 306-40</b>                              |           | Retaining cylindrical assemblies, high-temperature resistant, slow-curing; medium viscosity, high strength, hard to disassemble  | green       | M 20                      | 600 nt                                 | 0,15                            | 20 - 30                         | 30 - 40                          | 15 - 30 (2.175 - 4.350)                   | ca. 240                               | ca. 24                             | -60 to +200 (-76 to +392)        |   |
| <b>AN 306-41</b>                              |           | Retaining cylindrical assemblies, medium viscosity, medium strength, disassembly with normal tools   | yellow      | M 20                      | 550 nt                                 | 0,12                            | 12 - 15                         | 17 - 22                          | 8 - 12 (1.160 - 1.740)                    | 10 - 20                               | 3 - 6                              | -60 to +150 (-76 to +302)        |   |
| <b>AN 306-48</b>                              |           | Retaining cylindrical assemblies, high-temperature resistant; drinking water <sup>1</sup> approval, BAM <sup>3</sup> , medium viscosity, high strength, hard to disassemble  | green       | M 20                      | 550 nt                                 | 0,15                            | 30 - 35                         | 55 - 70                          | 25 - 35 (3.625 - 5.075)                   | ca. 5                                 | 2 - 4                              | -60 to +175 (-76 to +347)        |   |
| <b>AN 306-60</b>                              |           | Assembly of cylindrical parts; ideal for repair of worn out bearings, bushes and damaged seats of bearings as well as for larger gaps up to 0.5 mm, high viscosity, high strength, hard to disassemble                       | silver      | R 2"                      | 150.000 - 900.000 ht                   | 0,50                            | 35 - 45                         | 10 - 20                          | 25 - 30 (3.625 - 4.350)                   | 15 - 30                               | 3 - 6                              | -60 to +150 (-76 to +302)        |   |
| <b>Flange sealing, gasketing</b>              |           |  |             |                           |  |                                 |                                 |                                  |   |                                       |                                    |                                  |   |
| <b>AN 301-65</b>                              |           | Pipe and flange sealing (with PTFE) drinking water <sup>1</sup> approval, high viscosity, medium strength, disassembly with normal tools   | white       | M 80 R 3"                 | 180.000 - 300.000                      | 0,50                            | 4 - 8                           | 1 - 3                            | 2 - 6 (290 - 870)                         | 10 - 20                               | 24                                 | -60 to +150 (-76 to +302)        |   |
| <b>AN 301-72</b>                              |           | Pipe and flange sealing (with PTFE) drinking water <sup>1</sup> and DVGW <sup>2</sup> approval, high viscosity, medium strength, disassembly with normal tools   | white       | M 80 R 3"                 | 15.000 - 60.000 ht                     | 0,30                            | 5 - 10                          | 4 - 6                            | 5 - 7 (725 - 1.015)                       | 15 - 30                               | 6 - 12                             | -60 to +200 (-76 to +392)        |   |
| <b>AN 305-10</b>                              |           | Gasketing of flanges, gearboxes and motor housings, high-temperature resistant; AGA <sup>4</sup> approval, high viscosity, high strength, hard to disassemble  | orange      | ---                       | 70.000 - 300.000 ht                    | 0,50                            | 18 - 25                         | 15 - 25                          | 5 - 10 (725 - 1.450)                      | 15 - 30                               | 6 - 12                             | -60 to +200 (-76 to +392)        |   |
| <b>AN 305-18</b>                              |           | Flange sealing and gasketing, large gap-filling with instant seal; high viscosity, high strength, hard to disassemble  | red         | ---                       | 80.000 - 500.000 ht                    | 0,50                            | 12 - 18                         | 18 - 24                          | 8 - 13 (1.160 - 1.885)                    | 10 - 20                               | 3 - 6                              | -60 to +200 (-76 to +392)        |   |
| <b>AN 305-67</b>                              |           | Pipe and flange sealing (with PTFE) high viscosity, low strength   | white       | M 80 R 3"                 | 17.000 - 410.000 ht                    | 0,60                            | 3 - 5                           | 2 - 4                            | 6 - 8 (870 - 1.160)                       | 120 - 240                             | 24 - 72                            | -50 to +175 (-58 to +347)        |   |
| <b>AN 305-72</b>                              |           | Pipe and flange sealing (with PTFE), instant seal, drinking water <sup>1</sup> , DVGW <sup>2</sup> and AGA <sup>4</sup> approval, high viscosity medium strength, disassembly with normal tools                              | white       | M 80 R 3"                 | 17.000 - 50.000 ht                     | 0,40                            | 7 - 10                          | 2 - 4                            | 4 - 6 (580 - 870)                         | 20 - 40                               | 5 - 10                             | -60 to +150 (-76 to +302)        |   |
| <b>AN 305-73</b>                              |           | Gasketing of flanges, gearboxes and motor housings, elastic; high viscosity, low strength, easy disassembly  | light green | ---                       | 17.000 - 50.000 ht                     | 0,30                            | 6 - 10                          | 2 - 5                            | 4 - 6 (580 - 870)                         | 20 - 40                               | ca. 12                             | -60 to +150 (-76 to +302)        |   |
| <b>AN 305-74</b>                              |           | Gasketing of flanges, gearboxes and motor housings, universal type, high-temperature resistant; high viscosity, high strength, hard to disassemble   | orange      | ---                       | 30.000 - 100.000 ht                    | 0,50                            | 16 - 24                         | 5 - 10                           | 5 - 10 (725 - 1.450)                      | 15 - 30                               | ca. 12                             | -60 to +180 (-76 to +356)        |   |

**Recommended additional products**

| Product                             | Application  | Content           | Colour     | Odour    |
|-------------------------------------|--|-------------------|------------|----------|
| <b>Thread Sealing Cord DF 175</b>   | For permanent and safe sealing of almost all metal- and plastic threads.   | Mastic can 175 ml | white      | no odour |
| <b>Plast-o-Seal®</b>                | For sealing the smoothly treated flanges of machine, gearbox and motor casing flanges. Improves the performance of both old and new gaskets.                                   | 90g/ 120g 300g    | blue       | no odour |
| <b>Surface Cleaner</b>              | For cleaning and degreasing of surfaces to be joined or sealed with WEICON adhesives and sealants.   | 150 ml 400 ml     | colourless | solvent  |
| <b>Sealant and Adhesive Remover</b> | Removes residues of cured sealants and adhesives as well as oil, charcoal, lacquers and paints.  | 400 ml            | milky      | solvent  |
| <b>Activator F Spray</b>            | For activating passive surfaces, like e.g. aluminium, stainless steel, zinc, chrome, etc. as well as in case of low ambient temperatures (less than +10°C) and for large gaps. | 200 ml 1000 ml    | turquoise  | solvent  |
| <b>Hand Protective Foam</b>         | Waterproof   |                   |            |          |